



## **RIO TEX 2000**

### **MATT EMULSION COATING**

#### **DESCRIPTION:**

High quality matt acrylic emulsion under coat that has the following exceptional features:

- Exceptional non-yellowing whiteness and brightness.
- Excellent adhesion.
- Excellent hiding power.
- Chalking resistant.

#### **Technical data:**

Color White.

Specific Gravity  $1.5 \pm 0.1$  gm. /cm<sup>3</sup>.

Viscosity  $125 \pm 15$  KU/ 25° C.

Drying Time

- Surface Dry: within 30 minutes.
- Through Dry: within 3 hours.

Film Thickness 120 – 200 micron.

Dilution using Fresh water

Thinning ratio max. 15%.

#### **Theoretically spreading rate:**

3-5 m<sup>2</sup>/l at dry film thickness 30 microns (the porosity of the surface, type of surface, application method, film thickness affect the mentioned spreading values)

#### **Application:**

- Clean surface well from dust and other dirt.
- New and gypsum surfaces at 1<sup>st</sup> apply :  
1-should be washed with water  
2-apply 1 coat using Rio Seal
- apply 3 layers of Rio Filler Putty
- Apply 2 coat of Rio Tex 2000 as under coat.

#### **Validity & storage conditions:**

- 24 months from production date in dry place & away from direct exposure to sun light in originally closed containers.

#### **Safety Precautions:**

The MSDS of the products expresses necessary data for safety storage& handling.

#### **Country of origin:**

Egypt

28-Jul-18

Headquarter: 61 El Mariotiah Road, besides Siag Hotel, Giza, Egypt.

Factory: 1<sup>st</sup> Industrial Zone, 6<sup>th</sup> Of October, Giza, Egypt.

Tel.: +20 1146448884

[www.kaizenpaints.com](http://www.kaizenpaints.com)

[info@kaizenpaints.com](mailto:info@kaizenpaints.com)