

RIO GLOSS GLOSSY EMULSION COATING

DESCRIPTION:

High quality glossy emulsion coating that has the following exceptional features:

- Available in many degrees of gloss
Egg Shell-Silk-Semi Gloss-High Gloss
- Exceptional non-yellowing whiteness and brightness.
- Alkali & Water resistance.
- Highly washable.
- Excellent hiding power.
- Chalking resistant.

Technical data:

Color White.

Specific Gravity 1.2 ± 0.1 gm. /cm³.

Viscosity 120 ± 15 KU/ 25° C.

Drying Time

- Surface Dry: within 30 minutes.
- Through Dry: within 3 hours.

Film Thickness 120 – 200 micron.

Dilution using Fresh water

Thinning ratio max. 10%.

Theoretically spreading rate:

10-12 m²/l at dry film thickness 30 microns
(the porosity of the surface, type of surface, application method, film thickness affect the mentioned spreading values)

Application:

- Clean surface well from dust and other dirt.
- New and gypsum surfaces at 1st apply :
1-should be washed with water
2-apply 1 coat using Rio Seal
- apply 3 layers of Rio Filler Putty

- Apply 1 coats of Rio Tex as undercoat.
- Apply 1 coats of Rio Flat as undercoat.
- Apply 2 coats of Rio Gloss as topcoat.

Validity & storage conditions:

- 24 months from production date in dry place & away from direct exposure to sun light in originally closed containers.

Safety Precautions:

The MSDS of the products expresses necessary data for safety storage& handling.

Country of origin:

Egypt

