

RIO LACK

SYNTHETIC ENAMEL COATING

DESCRIPTION:

High quality glossy & matt synthetic enamel coating that has the following exceptional features:

- Available in glossy and matt types
- Good non-yellowing brightness.
- Weathering & Water resistance.
- Available in many colors.
- Excellent hiding power.
- Chalking resistant.

Technical data:

Color White, Black, Blue, Red, Yellow,
Brown, Green,...etc.

Specific Gravity

1.05 ± 0.2 gm. /cm³.(Glossy type)

1.5 ± 0.2 gm. /cm³.(Matt type)

Drying Time

- Surface Dry:
within 6 hours (glossy type)
within 45 min. (Matt type)
- Through Dry: within 12 hours.

Film Thickness 120 – 200 micron.

Dilution using white spirits

Thinning ratio max. 10-25%.

Theoretically spreading rate:

- Glossy type 10-12 m²/l at dry film thickness 30 microns (the porosity of the surface, type of surface, application method, film thickness affect the mentioned spreading values)
- Matt type 5-7 m²/l at dry film thickness 30 microns (the porosity of the surface, type of surface, application method, film thickness affect the mentioned spreading values)

Application:

- Clean surface well from dust and other dirt.
- New and gypsum or wall surfaces at 1st apply :
1-should be washed with water
2-apply 1 coat using Rio Seal
- apply 3 layers of Rio Filler Putty
- Apply 1 coats of Rio Lack Matt as undercoat.
- Apply 2 coats of Rio Lack Gloss as topcoat.
- For wood surfaces: Apply 2 coats of Rio Lack Matt as undercoat, then Apply 2 coats of Rio Lack Gloss as topcoat.

Validity & storage conditions:

- 24 months from production date in dry place & away from direct exposure to sun light in originally closed containers.

Safety Precautions:

The MSDS of the products expresses necessary data for safety storage& handling.

Country of origin: Egypt

